


## Q-View

Let us  
print your  
part!<sup>1</sup>



EnvisionTEC's quick building Q-View C resin is ideal for providing fast design verification models. This exciting material is capable of impressive print speeds on EnvisionTEC's cDLM (Continuous Digital Light Manufacturing) 3D printers.

Designers and manufacturers will have the ability to hold models in their hands in record time for final fit and design verification. It can also be used as a pattern when built in high resolution to make silicone molds.

Material Properties <sup>2</sup>		
Testing Method	Description	Value
ASTM D 638-10	Tensile strength at break	5160 psi
ASTM D 638-10	Tensile elongation at break	3.7%
ASTM D 638-10	Tensile modulus	217 ksi
ASTM D 790	Flexural strength at break	11,800 psi
ASTM D 790	Flexural modulus	332 ksi
ASTM D 2240, Method B	Durometer D hardness	85 D Shore
ASTM D 648-07	Heat deflection temperature at 264 psi	43.3°C
ASTM D 648-07	Heat deflection temperature at 66 psi	70°C

### Recommended 3D Printer Family<sup>3</sup>

Perfactory Family, Micro Family, cDLM Family

<sup>1</sup> Learn more at [EnvisionTEC.com/printmypart](https://www.envisiontec.com/printmypart)

<sup>2</sup> All data provided is preliminary and must be verified by the individual user

<sup>3</sup> May not be suitable for all machine models within a 3D printer family. Please refer to specific model online for compatibility.